



Technical data for Gibo Plast A/S

ABS

[CAS: 9003-56-9](#)

Listed data is the minimum requirements for the all products in that specific kategori, ABS Regrind, ABS 500, ABS 510, ABS 520, unless marked with (Max). Data with a tolerance is marked by(±X%). All products are extruded.

GENERAL

Property	Method	Unit	ABS Regrind	ABS 500	ABS 510	ABS 520
Density (±2%)	ISO 1183	g/cm ³	1.08	1.07	1.07	1.04
Water absorption (Max)	DIN EN ISO 62 Method 1	%	0.30	0.30	0.30	0.30
Ball indention hardness	ISO 2039-1	MPa	-	90	85	65
Flammability	UL 94	-	HB	HB	HB	HB

MECHANICAL

Property	Method	Unit	ABS Regrind	ABS 500	ABS 510	ABS 520
Tensile strength	ISO 527-2	MPa	32	46	-	-
Elongation at break	ISO 527-2	%	35	40	15	9
Tensile modulus	ISO 527-2	MPa	2100	1595	1900	1900
Flexural strength	ISO 178	MPa	-	70	60	56
Flexural modulus	ISO 178	MPa	-	2100	-	-
Yield stress	ISO 572-1	MPa	32	24	40	38
Impact strength @23°C (Charpy notched)	ISO 179-1	KJ/m ²	13	9	23	36

THERMAL

Property	Method	Unit	ABS Regrind	ABS 500	ABS 510	ABS 520
Vicat temperature (B 50) (±1%)	ISO 306	°C	-	100	100.5	102
Service temperature (Continuous use)	-	°C	85	85	85	85
Max. temperature (Short term use)	-	°C	100	100	100	100

Gibo Plast A/S | Ferrodanvej 14 | DK-6900 Skjern | Tlf: +45 8782 8700 | Fax: +45 8725 1110 | E-mail: post@giboplast.com

The technical data have been collected and categorised by Gibo Plast A/S in good faith. They are non-binding and do not represent a material specification or assurance of specific properties. We explicit reserve the right to change or update these instructions at any time.

Further processing and use of the products can have various impact on the products. Therefore, Gibo Plast A/S, does not guarantee or warrant for the fitness, suitability or adequacy of the products for any purpose intended by the purchaser or any third person and shall have no liability whatsoever in this respect. The purchaser has the obligation to test the products and determine itself is the products are fit for the intended use.

Gibo Plast A/S shall neither nor indirectly, indemnify and hold harmless purchaser or any third person in the event of any third-party claims related to the infringement of intellectual property rights.